

Flame Retardant Test Method



IEC 332. 1 & IEC 332.2 TEST METHOD

Hanging core/cable exposed to flame influence.

Temperature range: 800°C

Single core cable

- ◆ IEC 332.2 Test Duration : 20 secs
- ◆ IEC 332.1 Test Duration : 1 to 2 mins

IEC 332. 3 TEST METHOD

Bunched Cable Test under fire conditions

3 Categories - A, B and C

Bundled cables placed in oven, exposed to continuous fire influence.

Temperature range: 800°C

Category	Amount of Burning Material (Litres/m)	Burning Time (Min)
A	7	40
B	3.5	40
C	1.5	20

